



Chemical Resistance Ratings for Spal-Pro RS 88 Polyurea

<u>Chemical</u>	<u>Exposure</u>	<u>Chemical</u>	<u>Exposure</u>
Acetic Acid	A	Sulfuric Acid:	
Acetone	A	5%	A
Amomonium Hydroxide:		10%	A
10%	A	Toluene	C
20%	A	Vinegar (5% acetic acid)	A
Brake Fluid	C	Water:	
Bleach, 10%	NR	10% NaCl/ Water	A
Deisel Fuel	A	10% Sugar/ Water	A
Dimethyl Formamide	NR	Water	A
Gasoline, unleaded	A		
Hexane	A		
Hot tub Water, brominated	A		
Hydraulic Fluid	A		
Hydraulic Oil	A		
Hydrochloric Acid:			
5%	A		
10%	A		
JEFFAMINE® D-400	NR		
Methanol	A		
5% Methanol/ Gasoline	A		
2-Methylbutane	A		
Motor Oil	A		
MTBE	A		
5% MTBE/ Gasoline	A		
Phosphoric Acid:			
10%	A		
Potassium Hydroxide:			
10%	A		
20%	A		
Propolene Carbonate	C		
Sodium Hydroxide:			
10%	A		
20%	A		
50%	A		
Sulfuric Acid, conc.*	NR		

Code Key:

A - Acceptable - No Visible Damage
 C - Conditional - Please Call
 NR- Not Recommended

* - Less than 24 hours exposure

Testing Standard:
 ASTM-D 3912, 77° F (25°C)

For Questions or Additional Information Contact Us at
800-223-6680
www.metzgermcguire.com