



## Chemical Resistance Ratings for Rapid Refloor LV Repair Product

<u>Chemical</u>	<u>Exposure</u>
Acetic Acid	A
Acetone	A
Ammonium Hydroxide:	
10%	A
20%	A
Brake Fluid	C
Bleach, 10%	NR
Deisel Fuel	A
Dimethyl Formamide	NR
Gasoline, unleaded	A
Hexane	A
Hot tub Water, brominated	A
Hydraulic Fluid	A
Hydraulic Oil	A
Hydrochloric Acid:	
5%	A
10%	A
JEFFAMINE® D-400	NR
Jet Fuel	A
Methanol	A
5% Methanol/ Gasoline	A
2-Methylbutane	A
Motor Oil	A
MTBE	A
5% MTBE/ Gasoline	A
Phosphoric Acid:	
10%	A
Potassium Hydroxide:	
10%	A
20%	A
Propylene Carbonate	C
Sodium Hydroxide:	
10%	A
20%	A
50%	A
Sulfuric Acid, conc.*	NR

<u>Chemical</u>	<u>Exposure</u>
Sulfuric Acid:	
5%	A
10%	A
Toluene	C
Vinegar (5% acetic acid)	A
Water:	
10% NaCl/ Water	A
10% Sugar/ Water	A
Water	A

### Code Key:

A - Acceptable - No Visible Damage  
 C - Conditional - Please Call  
 NR - Not Recommended

\* - Less than 24 hours exposure

**Testing Standard:**  
 ASTM-D 3912, 77° F (25°C)

Updated 9/12

For Questions or Additional Information Contact Us at

**800-223-6680**

[www.metzgermcguire.com](http://www.metzgermcguire.com)